
AUBURN PRODUCT NEWS

Auburn Manufacturing Company

29 Stack Street

Middletown, CT 06457

Tel: 860-346-6677, Fax: 860-346-1334

website: www.auburn-mfg.com

email: info@auburn-mfg.com

TN-9000 – Thermo-Tork® Non-Asbestos Gasket Material

Specification Data Sheet

F729900E33M9

Description

TN-9000 has a fully cured nitrile butadiene rubber binder with Aramid fiber. It has good tensile strength, low creep relaxation, and excellent fuel and oil resistance. It is intended for applications with high flange pressures and temperatures, with short duration maximum temperatures up to 400°C (750°F).

Property:	Specification:	Method:
Density , g/cc (lb/cu. ft.)	1.44 (90) (min.)	ASTM F 1315
Compressibility , % (at 34.5Mpa)	7 – 17	ASTM F 36
Recovery , %	50 (min.)	ASTM F 36
Tensile Strength , AMD,Mpa (psi)	17.24 (2500) (min.)	ASTM F 152
Fluid Resistance , IRM903 Oil		ASTM F 146
Change in Tensile Strength, %	35 (max.)	
Change in Thickness, %	10 (max.)	
Change in Compressibility, %	30 (max.)	
Fluid Resistance , Fuel B		ASTM F 146
Change in Thickness, %	15 (max.)	
Change in Weight, %	20 (max.)	
Binder	Fully Cured Nitrile Butadiene	

Remarks and related documents:

Specification Values determined by test methods required for ASTM F-104. Type 7 materials.

Ordering Information: TN-9000 is available in thicknesses of .015", .020", .025", .031", .047" and .062", in rolls @ 40" wide continuous length or sheets @ 40" x 36". Anti-Stick coating is available and can be applied to one or both sides. **Auburn can die cut, stamp, slit-to-width, strip, sheet, or apply pressure sensitive adhesives to TN-9000 in accordance with your exact specifications.**

GASKETS • PADS • SEALS • BUSHINGS • SPACERS
