



# PRODUCT NEWS

## Auburn Manufacturing Company

29 Stack Street, Middletown, CT 06457  
Customer Service: (800) 427-5387  
Tel: (860) 346-6677 Fax: (860) 346-1334  
website: [www.auburn-mfg.com](http://www.auburn-mfg.com)  
email: [info@auburn-mfg.com](mailto:info@auburn-mfg.com)

## Soft Ceramic-Filled Silicone Elastomer Gap Filler

### TC100

#### Gap Filler, Thermal Interface Materials

**ThermaCool® TC100 from Auburn** is an unsupported thermally conductive solid silicone rubber. This material offers thermal conductivity along with electrical isolation for heat transfer applications. TC100 can be used to fill air gaps between PC boards and heat sinks where a firm, robust material is needed.

**ThermaCool TC100** viscoelastic core is specially designed to provide the following features:

- Filled silicone rubber material that does not require curing
- Formulated to provide clean release from most surfaces
- Material is rigid enough to be easily die cut
- Gap filler can be readily repositioned
- Ideal for applications where gaps are  $>.020$  and can accommodate high pressure force of 100 psi
- Provides good vibration isolation of components that also require thermal transfer

#### Available Sizes

Standard thickness: .025, .031, .050 and .063 in. (.64, .79, 1.27 and 1.6 mm)

Master roll size: 18 in. x continuous yard length

Master sheet size: 18 x 36 in. (457 x 914 mm)

#### Auburn Manufacturing Co.

Your Direct Source for Custom  
Gaskets and Seals Die Cut to  
Your Exact Specifications

#### APPLICATIONS

- Telecommunications
- Computers
- CD-ROM cooling
- Automotive electronics
- Electrical insulation
- Military
- Medical
- Heat pipe assemblies
- Electronic modules for devices

## ThermaCool TC100 — Properties

Performance tests are run using standard test procedures.

The values presented are typical values and should not be used for specification purposes.

Property	Test Method	Typical Value
Color	Visual	Light Blue
Thickness, nominal in.	ASTM D374	.025, .032, .062
Thermal Conductivity: W/mK	ASTM E1530	1.3
Thermal Impedance: °C in.2 /W (1/16")	ASTM E1530	1.25
Break Strength: psi	ASTM D412	250
Elongation: %	ASTM D412	200
Hardness: Shore A	ASTM D2240	65
Dielectric Strength: volts/mil	ASTM D149	> 250
Volume Resistivity: ohm-cm	ASTM D257	5x10 <sup>15</sup>
Operating Temperature: °F	-----	-80 to +400
UL Listing Recognition	UL 94	HB

### Important Instructions

Because Auburn cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use.

### Shelf Life

10 years after the date of sale for base material when stored in original packaging at temperatures up to 95°F (35°C) and 70% relative humidity.